

DAUNTLESS



Mocha



Doe



Ocean Grey



Chestnut



Black

DAUNTLESS SPECIFICATIONS

DESCRIPTION

Weight (<i>linear yard</i>)	30.0 oz
Width	54"
Thickness	0.97 mm
Gauge	0.039
Surface Composition	100% PVC

GENERAL TREATMENTS

UV Resistance (<i>CFFA-2/ASTM G26-96 Method C</i>)	300 Hours
Cold Crack (<i>CFFA-6 Federal Standard No. 191A-Method 5874</i>)	-10° F
Sulfide Stain Resistance	Resilience ^{SR}

PHYSICAL PROPERTIES

Abrasion	250,000+	Cycles			(<i>CFFA-1A/Method ASTM D 4157-10</i>)
Tear Strength	11.9	Warp	15.4	Fill	(<i>CFFA-16/ASTM D2261-07c</i>)
Breaking Strength	95	Warp	73	Fill	(<i>CFFA-17/ASTM D751-06</i>)
Seam Strength	67	Warp	43	Fill	(<i>CFFA-14/Method ASTM D751-06</i>)
Crocking	5	Dry	5	Wet	(<i>AATCC-Method 8-2007</i>)

FLAME TREATMENTS

California Technical Bulletin 117-2013	Pass
UFAC Class 1	Pass
UIFMA CS-191-53, Section 3	Pass
UFPA 260	Pass

